

| | | |
|-------------------------------------|-----------------------------------|--|
| Product | Name | Organoid® BLIATNPRACHT light on flax backing |
| | Article number | BLIPRT2050FVPRW |
| | Producer | ORGANOID TECHNOLOGIES GMBH Nesselgarten 422 / Top 5 A-6500 Fließ Österreich |
| Description and applications | Name | Organoid® BLIATNPRACHT light on flax backing |
| | Description | Natural plant Material in low density on natural flax backing produced climate neutral in Tyrol |
| | Applications | As wallpaper As a compound in wood-working |
| Plant material and density | Plant material | Red and blue cornflowers, roses, sunflowers, and light green moss |
| | Density | Light, loosely spread, backing material is part of the design |
| Size and weight | Size | Rolled goods, width 1 360 mm |
| | Thickness | 0.2 mm |
| | Weight | 125 g/m ² |
| Product requirements | Hardly inflammable Food-safety | B-s1, d0 in accordance with EN ISO 13501-01 Binding agent safe for usage in contact with food in accordance with EU-regulation 1935/2004 |
| Backing material | Material Properties | Natural, non-woven flax fleece Unbleached and breathable from a renewable material Contains 100% flax Certified OEKO-TEX 100 Tensile strength in accordance with ISO 9073-3: MD N/5cm 65 CD N/5cm 45 |
| Technical implementation | Cut | Use scissors, a cutter or a plotter |
| | Edges | Allow for imperfections 1-2 mm around the edges |
| | How to install | <u>As wallpaper:</u> - Wall-pasting technique: Apply glue directly on the wall, apply wallpaper vertically and press on using a rubber roller - Double cut: Each panel overlaps with the one next to it (approx. 2 cm) - Free match: The naturally scattered materials do not require matching patterns between panels |

As a compound in wood-working

-Process with normal wood-working machinery

-Glue (e.g. white glue) is applied onto the wooden materials, as the fleece absorbs moisture and glue stains may appear on the front if glue is applied to the fleece

-Cover the natural surface with the enclosed separating paper

-Guidelines:

Max. pressing temperature. 60°C

Max. pressure 1 kg/cm²

Glue application: approx. 100 g/m²

Pressing time: approx. 15 minutes

Pre-trials and tests are recommended

Glue recommendations As wallpaper:

- Methylan Direct Kleister Vliestapeten
- Pufas Glasgewebe- und Vlieskleber GK,
- Pufas Sicherheitskleister SK,
- AURO Wandbelagskleber Nr. 391 (ecological glue),
- Universalkleber für Vliestapeten
- Nr. 380 (ecological glue)

As a compound in wood-working:

- White glue

Pay attention to

Surface must be clean, dry, weight-bearing, evenly absorbent, smooth, dust-free and neutral in colour. Recently plastered walls must be fully dried. Highly absorbent walls must be prepared with a suitable base.

For sensitive wood-working applications, use a counter-balance (enclosed on request).

Symmetrical construction is recommended, which means using the same surface on the front and back side.

Acclimatisation of Organoid natural surfaces:

- Bring product to room temperature before unpacking

- Store product protected from light, at about 20°C and 30-60 % relative humidity.

- Storage:

- Rolled goods: hanging system (e.g.

paternoster)

- Single panels: horizontal position (e.g. drawer system)

Processing guidelines
available at:

<https://organoid.corestad.com/verarbeitung/>
(= current link)