

Product	Name	Organoid® HOPFN medium on golden paper
	Article number	HOPBLI0065GTARW
	Producer	Address ORGANOID TECHNOLOGIES GMBH Nesselgarten 422 / Top 5 A-6500 Fließ Österreich
Description and applications	Name	Organoid® HOPF medium on golden paper
	Description	Natural plant Material in medium density on golden paper produced climate neutral in Tyrol
	Applications	As paper As a compound in wood-working
Plant material and density	Plant material	Hop petals
	Density	Medium, loosely spread, backing material is part of the design
Size and weight	Size	Rolled goods, width 1 360 mm
	Thickness	0.2 mm
	Weight	190 g/m ²
Product requirements	Food-safety	Binding agent safe for usage in contact with food in accordance with EU-regulation 1935/2004
Backing material	Material	Golden paper
	Properties	Shimmering
Technical implementation	Cut	Use scissors, a cutter or a plotter
	Edges	Allow for imperfections 1-2 mm around the edges
	How to install	<u>As a compound in wood-working</u> -Process with normal wood-working machinery -Glue (e.g. white glue) is applied onto the wooden materials, as the fleece absorbs moisture and glue stains may appear on the front if glue is applied to the fleece -Cover the natural surface with the enclosed separating paper -Guidelines: Max. pressing temperature. 60°C Max. pressure 1 kg/cm ² Glue application: approx. 100 g/m ² Pressing time: approx. 15 minutes
Pre-trials and tests are recommended		

Glue recommendations	As a compound in wood-working: White glue
Pay attention to	<p>Surface must be clean, dry, weight-bearing, evenly absorbent, smooth, dust-free and neutral in colour. Recently plastered walls must be fully dried. Highly absorbent walls must be prepared with a suitable base.</p> <p>For sensitive wood-working applications, use a counter-balance (enclosed on request). Symmetrical construction is recommended, which means using the same surface on the front and back side.</p> <p>Acclimatisation of Organoid natural surfaces:</p> <ul style="list-style-type: none"> - Bring product to room temperature before unpacking - Store product protected from light, at about 20°C and 30-60 % relative humidity. - Storage: <ul style="list-style-type: none"> • Rolled goods: hanging system (e.g. paternoster) • Single panels: horizontal position (e.g. drawer system)
Processing guidelines available at:	https://organoid.corestad.com/verarbeitung/ (= current link)